

Material Data Sheet: Z-ULTRAT

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cm <sup>3</sup>	9.013 lbs/gal	ASTM D792
Density	1.08 g/cm <sup>3</sup>	9.013 lbs/gal	ISO 1183
Maximum Moisture Content	0.001	0.001	
Linear Mold Shrinkage, Flow	0.0050 - 0.0080 cm/cm Thickness 3.20 mm	0.0050 - 0.0080 in/in Thickness 0.126 in	ASTM D955
Melt Flow	13.7 g/10 min Load 3.80 kg, Temperature 230 °C	0.03 lb/10 min Load 8.38 lb, Temperature 446 °F	ASTM D1238 (I)
	12 g/10 min Load 5 kg, Temperature 220 °C	0.03 lb/10 min Load 11 lb, Temperature 428 °F	
	42 g/10 min Load 10 kg, Temperature 220 °C	0.09 lb/10 min Load 22 lb, Temperature 428 °F	ISO 1183
Melt Viscosity	1870 1000 sec <sup>-1</sup> , Temperature 240 °C	1870 1000 sec <sup>-1</sup> , Temperature 464 °F	ASTM D3825 (I)
Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	42 MPa Thickness 3.20 mm	6091 psi Thickness 0.126 in	5mm/min; ASTM D638
	42 MPa Thickness 3.20 mm	6091 psi Thickness 0.126 in	50mm/min; ISO 527
Tensile Strength, Break	30 MPa Thickness 3.20 mm	4351 psi Thickness 0.126 in	5mm/min; ASTM D638
	30 MPa Thickness 3.20 mm	4351 psi Thickness 0.126 in	50mm/min; ISO 527
Elongation at Break	21 % Thickness 3.20 mm	21 % Thickness 0.126 in	5mm/min; ASTM D638
	21 % Thickness 3.20 mm	21 % Thickness 0.126 in	50mm/min;
Elongation at Yield	2.3 % Thickness 3.20 mm	2.3 % Thickness 0.126 in	5mm/min; ASTM D638
	2.6 % Thickness 3.20 mm	2.6 % Thickness 0.126 in	50mm/min; ISO 527

Tensile Modulus	1.95 GPa Thickness 3.20 mm	283 ksi Thickness 0.126 in	1mm/min; ASTM D638
	1.95 GPa Thickness 3.20 mm	283 ksi Thickness 0.126 in	1mm/min; ISO 527
Flexural Yield Strength	50 MPa Thickness 3.20 mm	7252 psi Thickness 0.126 in	1.3mm/min; ASTM D790
	51 MPa Thickness 3.20 mm	7397 psi Thickness 0.126 in	2mm/min; ISO 178
Flexural Modulus	2.02 GPa Thickness 3.20 mm	293 ksi Thickness 0.126 in	1.3mm/min; ASTM D790
	2.03 GPa Thickness 3.20 mm	294 ksi Thickness 0.126 in	2mm/min; ISO 178
Izod Impact, Notched	0.60 J/cm Thickness 3.20 mm, Temperature -30.0 °C	1.05 ft-lb/in Thickness 0.126 in, Temperature -22.0 °F	ASTM D256
	1.8 J/cm Thickness 3.20 mm, Temperature 23.0 °C	3.3 ft-lb/in Thickness 0.126 in, Temperature 73.0 °F	
	5 kJ/m2 80x10x4 mm, Temperature -30.0 °C	3.2 ft-lb/in <sup>2</sup> 3.15x0.394x0.157 in, Tempe- rature -22.0 °F	ISO 180/1A
	12 kJ/m2 80x10x4 mm, Temperature 23.0 °C	7.7 ft-lb/in <sup>2</sup> 3.15x0.394x0.157 in, Temperature 73.0 °F	
Thermal Properties	Metric	English	Comments
Vicat Softening Point	128.0 °C Load 5.00 kg	262 °F Load 11.0 lb	B/50; ASTM D 1525
	128.0 °C Load 5.00 kg	262 °F Load 11.0 lb	B/50; ISO 306
	130.0 °C Load 5.00 kg	266 °F Load 11.0 lb	B/120; ISO 306
UL RTI, Electrical	60.0 °C Thickness ≥1.50 mm	140 °F Thickness ≥0.0591 in	
	60.0 °C Thickness ≥3.00 mm	140 °F Thickness ≥0.118 in	
UL RTI, Mechanical with Impact	60.0 °C Thickness ≥1.50 mm	140 °F Thickness ≥0.0591 in	
	60.0 °C Thickness ≥3.00 mm	140 °F Thickness ≥0.118 in	

UL RTI, Mechanical without Impact	60.0 °C Thickness ≥1.50 mm	140 °F Thickness ≥0.0591 in	
	60.0 °C Thickness ≥3.00 mm	140 °F Thickness ≥0.118 in	
Flammability, UL94	HB Thickness ≥1.60 mm	HB Thickness ≥0.0630 in	
	HB Thickness ≥3.20 mm	HB Thickness ≥0.126 in	
Deflection Temperature at 0.45 MPa (66 psi)	112 °C Thickness 3.20 mm	234 °F Thickness 0.126 in	Unannealed; ASTM D648
Deflection Temperature at 1.82 MPa (264 psi)	98 °C Thickness 3.20 mm	208 °F Thickness 0.126 in	Unannealed; ASTM D648
Deflection Temperature at 0.45 MPa (66 psi)	102 °C 120x10x4 mm sp=100 mm	216 °F 4.72x0.394x0.157 in sp=3,937 in	ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	90 °C 120x10x4 mm sp=100 mm	194 °F 4.72x0.394x0.157 in sp=3,937 in	ISO 75/Ae

The information presented are typical values intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Final properties of the material can be impacted (+/-) by part design, end-use conditions, test conditions, etc. Actual values will vary with build conditions. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions, or end-use. Each user is responsible for determining that the Zortrax material is safe, lawful and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. Zortrax makes no warranties of any kind, express or implied including but not limited to the warranties of merchantability, fitness for a particular use.

**Contact**

Office: [office@zortrax.com](mailto:office@zortrax.com)  
 Sales Department: [sales@zortrax.com](mailto:sales@zortrax.com)  
 Support Center: [support@zortrax.com](mailto:support@zortrax.com)

**Zortrax S.A.**

Wyszynskiego 1/219  
 10-457 Olsztyn, Poland  
 NIP: 7393864289  
 REGON: 281551179

Entered in the Register of Entrepreneurs of the National Court Register kept by the District Court in Olsztyn, VIII Commercial Division of the National Court Register, under KRS number 0000564079, with a share capital of PLN 6 962 500 paid in full.

## Material Safety Data Sheet: Z-ULTRAT

**1. CHEMICAL PRODUCT AND COMPANY IDENTIFICATION****Supplier:**

Zortrax S.A.  
Wyszynskiego 1/219  
10-457 Olsztyn  
Poland

**Prepared by:**

University of Science and Technology Beijing  
No.1, Fuhe Street, Tongzhou District  
101149 Beijing, China  
Emergency phone: +86 10 89534415/+288

**In order:**

Zortrax S.A.  
Wyszynskiego 1/219  
10-457 Olsztyn  
Poland

Material name: **ABS (Acrylonitrile Butadiene Styrene Terpolymer)**

Chemical type: **Thermoplastics**

Material trade name: : **Z-ULTRAT**

**2. HAZARDS IDENTIFICATION****a. Threshold Limit - Not established****b. Effect of overexposure:**

- » Eye contact - Solid may cause irritation or corneal injury due to mechanical action
- » Skin Contact - Essentially non irritating to skin, mechanical injury only
- » Skin Absorption - Unlikely due to physical properties
- » Ingestion - Unlikely due to physical state
- » Inhalation - In case of breathing in small and non-ventilated room, fumes released from heated material may cause respiratory irritation
- » Chronic Effects - Not Available
- » Mutagenicity - Not Available

**3. COMPOSITION / INFORMATION ON INGREDIENTS**

- a. **ABS (Acrylonitrile-Butadiene-Styrene) - 90~100 % CAS:9003-56-9**
- b. **Typical Stabilizer - 0~5%**
- c. **Typical lubricants - 0~2%**
- d. **Mineral oil - 0~4% CAS:8042-47-5**
- e. **Tallow - 0~4% CAS:67701-27-3**
- f. **Wax - 0~4% CAS:110-30-5**
- g. **PC - 0~3% CAS: 111211-39-3**
- h. **Anti Oxydant - < 2%**

## 4. FIRST AID MEASURES

- a. Eye contact - Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor. Remove contact lenses, if present and easy to do.
- b. Skin contact - Essentially nonirritating to skin but rinse with copious water and soap . If skin irritation continues, consult a doctor. After contact with the molten product, cool rapidly with cold water. Do not pull solidified product away from the skin. Call a doctor immediately.
- c. Ingestion - Rinse out mouth and then drink plenty of water. Do not induce vomiting! If symptoms persist consult a doctor.
- d. Inhalation - In case of breathing, fumes released from heated material may cause respiratory irritation. In case of inhaling dense smoke, immediately remove a person to fresh air. If necessary, apply artificial respiration and seek medical attention immediately.
- e. Mutagenicity - Not Available.

## 5. FIRE FIGHTING MEASURES

- a. Flammable Properties
  - » Flash point - None
  - » Method used - Not applicable
  - » Auto ignition Temperature - Not applicable
- b. Extinguishing Media - Usually use water and use extinguishing media appropriate to surrounding conditions
- c. Special Fire Fighting Procedure - Cool Containers with water spray. In closed stores, provide fire fighter with self-contained breathing apparatus in positive pressure mode
- d. Usual Fire and Explosion Hazards - Irritating gases and dense smoke

## 6. ACCIDENTAL RELEASE MEASURES

- a. Avoid formation of dust
- b. Do not breathe dust
- c. Keep away from ignition sources
- d. Avoid contact with eyes
- e. Danger of slipping on leaked/spilled product
- f. Environmental precautions - Do not allow to enter sewers/ surface or ground water
- g. Methods and material for containment and cleaning up - Allow to solidify. Pick up mechanically

## 7. HANDLING AND STORAGE

### a. Handling

- » Avoid formation of dust
- » Keep spools lightly closed
- » Avoid spools from getting wet

### b. Storage

- » Kepp spools in a ventilated place
- » Avoid spools from getting wet

## 8. EXPOSURE CONTROLS / PERSONAL PROTECTION

- a. **Engineering Controls** - General ventilation should be sufficient for most conditions. Local exhaust ventilation may be necessary for some operations
- b. **Personal Protective Equipment:**
  - » Eye / Face Protection - Use safety glasses. If there is a potential for exposure to particles which could cause mechanical injury to the eye
  - » Skin Protection - No Precautions other than clean body-covering clothing should be needed
  - » Respiratory Protection - For most conditions, no respiratory protection should be needed, however, if handling at elevated temperatures without sufficient ventilation, use an approved air-purifying respirator.
- c. **Exposure Guideline** - Although some of the additives used in this product may have exposure guidelines, these additives are encapsulated in the product and no exposure would be expected under normal handling conditions

## 9. PHYSICAL AND CHEMICAL PROPERTIES

- a. **Appearance** - Solid
- b. **Odor** - Almost Odorless
- c. **Odor threshold** - No data available
- d. **pH** - Not applicable
- e. **Boiling Point** - Not applicable
- f. **Melting point** - Not applicable
- g. **Flash point** - Not determined
- h. **Flammability (solid, gaseous)** - Combustible at constant flame of fire
- i. **Ignition temperature** - Not determined
- j. **Decomposition temperature** - Not determined
- k. **Auto igniting** - Product is not self-igniting
- l. **Danger of explosion** - Not determined

- m. Oxidizing properties - Not determined
- n. Vapor pressure - Negligible
- o. Density - > 1g/cm<sup>3</sup> (> 8.345 lbs/gal)
- p. Evaporation rate - Negligible
- q. Solubility - Insoluble
- r. Miscibility - Insoluble
- s. Viscosity (dynamic/kinematic) - Not applicable

## 10. STABILITY AND REACTIVITY

- a. Stability - Stable under normal condition
- b. Chemical stability
- c. Thermal decomposition / conditions to be avoided:
  - » Avoid impact friction
  - » Avoid impact heat
  - » Avoid impact sparks
  - » Avoid impact electrostatic charges
- d. Conditions to avoid - No further relevant information available
- e. Incompatible materials - Strong oxidizing agents
- f. Hazardous decomposition products:
  - » Irritant gases/vapors
  - » Poisonous gases/vapors
  - » Smoke
  - » Carbon monoxide and carbon dioxide
  - » Hydrocarbons
  - » Hydrogen cyanide (prussic acid)
  - » Styrene
  - » Aldehyde
  - » Phenol
  - » Acrylonitrile
  - » Nitrogen oxides (NO<sub>x</sub>)

## 11. TOXICOLOGICAL INFORMATION

**a. LD/LC50 values that are relevant for classification:**

- » Oral LD50 > 5000 mg/kg (rat)
- » Dermal LD50 > 2000 mg/kg (rabbit)

**b. Primary irritant effect:**

- » On the skin: Dust particles may mechanically irritate the skin
- » On the eye: Dust particles may mechanically irritate the eye

**c. Sensitization - No sensitizing effects known**

**d. Subacute to chronic toxicity - No data available**

**e. Additional toxicological information - When used and handled according to specifications, the product does not have any harmful effects according to our experience and the information provided to us**

**f. Carcinogenic categories:**

- » IARC (International Agency for Research on Cancer) - None of the ingredients is listed
- » NTP (National Toxicology Program) - None of the ingredients is listed

## 12. ECOLOGICAL INFORMATION

**a. Environmental Fate:**

- » Movement & Partitioning - No bioconcentration is expected because of the high molecular weight (MW > 1000). In the terrestrial environment, material is expected to remain in the soil. In the aquatic environment, material will sink and remain in the sediment
- » Degradation & Persistence - This water insoluble polymeric solid is expected to be inert in the environment. Surface degradation is expected with exposure to sunlight. No appreciable biodegradation is expected

**b. Ecotoxicity - Not Expected to be acutely toxic, but pellets, if ingested by waterfowl or aquatic life, may mechanically cause adverse effects**

## 13. DISPOSAL CONSIDERATIONS

**a. Disposal : Do not dump into any sewers, on the ground, or into any body of water.**

All disposal methods must be in compliance with all Federal, State/Provincial and local laws and regulations. Regulations may vary in different locations. Waste characterizations and compliance with appliance laws are the responsibility solely of the waste generator.

**b. For unused & uncontaminated product, the preferred options include sending to a licensed, permitted:**

- » Recycler
- » Reclaim
- » Incinerator or other thermal destruction device



## 14. TRANSPORT INFORMATION

- a. **UN-Number:**
  - » DOT, ADR, IMDG, IATA – Not applicable
- b. **UN proper shipping name:**
  - » DOT, ADR, IMDG, IATA – Not applicable
- c. **Transport hazard class:**
  - » DOT, ADR, IMDG, IATA - Not applicable
- d. **Environmental hazards - Not applicable**
- e. **Special precautions for user - Not applicable**
- f. **Transport in bulk according to Annex II of MARPOL73/78 and the IBC Code - Not applicable**
- g. **Transport/Additional information - Not dangerous according to the above specifications**

## 15. REGULATORY INFORMATION:

- a. **Safety, health and environmental regulations/legislation specific for the substance or mixture US EPA TSCA:**
  - » CERCLA Section 103 (40CFR302.4) - Not Listed
  - » SARA Section 311/312 (40CFR370.21) – Not listed
  - » SARA Section 313 (40CFR372.65) – Not listed
  - » SARA Section 355 (extremely hazardous substances) – Not listed
  - » TSCA (Toxic Substances Control Act) – Not listed
  - » STATE REGULATIONS (California Proposition 65) – Not listed
- b. **EUROPEAN REGULATIONS:**
  - » EC NUMBER - Not assigned
  - » Directive 96/82/EC - does not apply
- c. **Carcinogenicity categories:**
  - » MAK (German Maximum Workplace Concentration) - None of the ingredients is listed
- d. **Product resp. its monomers are listed in:**
  - » Toxic Substance Control Act TSCA (USA)
  - » Canadian Domestic Substance List DSL
  - » Existing and New Chemical Substance List ENCS (Japan)
  - » Korean Existing Chemicals List KECL
  - » Australian Inventory of Chemical Substances AICS (Australia)
- e. **Chemical safety assessment - A Chemical Safety Assessment has not been carried out**

## 16. OTHER INFORMATION:

Product should be handled, stored, and used in accordance with the generally accepted industrial hygiene practices and in conformity with all the applicable legal regulations.

The information provided herein is based on the knowledge possessed at this present time from the view point of safety requirements. It should, therefore, not be construed as guaranteeing specific properties.

### Contact

Office: [office@zortrax.com](mailto:office@zortrax.com)

Sales Department: [sales@zortrax.com](mailto:sales@zortrax.com)

Support Center: [support@zortrax.com](mailto:support@zortrax.com)

### Zortrax S.A.

Wyszynskiego 1/219  
10-457 Olsztyn, Poland  
NIP: 7393864289  
REGON: 281551179

Entered in the Register of Entrepreneurs of the National Court Register kept by the District Court in Olsztyn, VIII Commercial Division of the National Court Register, under KRS number 0000564079, with a share capital of PLN 6 962 500 paid in full.

©2015, Zortrax S.A. All rights reserved. Zortrax, Zortrax M200, Z-ABS, Z-ULTRAT, Z-PCABS, Z-HIPS, Z-GLASS, Z-WOOD, Z-Suite, .zcode are trademarks of Zortrax.